



# SNOWSHOE LOUISA

**AFD:** 21.0  $\mu$   
**SD:** 4.4  $\mu$   
**CV:** 21.0 %  
**CF:** 96.1 %  
**Curve:** 41.7 Dg/mm  
**Min:** 19.3  $\mu$   
**Max:** 24.6  $\mu$   
**Staple:** 70.0 mm



# SNOWSHOE LOUISA

**AFD:** 21.0  $\mu$   
**SD:** 4.4  $\mu$   
**CV:** 21.0 %  
**CF:** 96.1 %  
**Curve:** 41.7 Dg/mm  
**Min:** 19.3  $\mu$   
**Max:** 24.6  $\mu$   
**Staple:** 70.0 mm



*Alpaca Fiber Testing USA*